

EBM

Coatings and Chemicals

Technical Data Sheet

EBM Wood Varnish Clear EN3000 EN3010 EN3030 EN3050 EN3090
Matt 10%Gloss 30%Gloss Semi-Gloss Gloss

Description : An alkyd based transparent Wood Varnish designed for protection of Native and tropical wood for interior and exterior use, for all kind of Application such as furniture chairs and frames.

Features:

1. Resistant to weathering conditions
2. Good yellowing resistance
3. Resistant to Mold and Fungi Formation
4. Good flow and leveling
5. High flexible

Physicals Properties:

| | | |
|--|---|--|
| Viscosity (Rot thinner at 25 ⁰ C) | : | 20 - 25 poise |
| Finish | : | Matt, 10% Gloss, 30%Gloss Semi-Gloss, Gloss |
| Flash Point | : | 37 ⁰ C |
| Specific Gravity | : | 0.93 kg/L |
| Solid by Weight | : | 50% ± 2 |
| Coverage rate | : | 12 - 14m ² /Liter |
| Dry film thickness | : | 30 - 40 micron |
| Shelf Life (dry and cool store) | : | One year |

Surface Preparation and Application Method:

1. The surface should be dry, free from dirt, oil, grease and powdery material.
2. For new surfaces, sand the entire surface until completely smooth.
3. Wipe the surface with **EBM TH White Spirit Thinner** to wet the wood.
4. For old surfaces, rub down any gloss surface present and remove the dust.
5. Apply one coats of **EBM Wood Varnish Clear** 50% thinned with **EBM TH White Spirit thinner** as a wood preservative first coat.
6. After drying, sand the surface with smooth sanding paper and clean the surface.
7. Apply two (2) coats of **EBM Wood Varnish Clear** in uniform layers.

Doha Factory for Paints and Chemicals

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: info@dohapaints.com. www.dohapaints.com

EBM

Coatings and Chemicals

Technical Data Sheet

EBM Wood Varnish Clear EN3000 EN3010 EN3030 EN3050 EN3090
Matt 10%Gloss 30%Gloss Semi-Gloss Gloss

Dilution and Application:

Type of thinner : EBM TH200
Percentage of thinning : 10 - 20% by volume
Nozzle orifice : 1.5 - 2 mm
Output pressure : 3 - 4 bar
Tools : Air spray gun
EBM Wood Varnish Clear can be also used by brush or roller.

Drying time (at 25°C):

Touch dry : 1 - 2 hours
Hard dry : 3 - 4 hours
A second coat be applied over night

Subsequent Coats:

NONE

Colors: Transparent

Packing: 18 Liter drum, 3.75 Liter Gallon, One Litter Can

Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 5°C and relative humidity less than 85%

After Application

- Clean all tools used immediately with TH 150 Thinner
- Close the cans after used
- Store in dry and cool area

For more information, don't hesitate to contact our Technical Department.

Doha Factory for Paints and Chemicals

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: info@dohapaints.com. www.dohapaints.com