

# EBM

Coatings and Chemicals

## Technical Data Sheet

### **EBM TX Sand Coat**

**TX4003**  
Sand Coat 1-2mm

**TX4004**  
Sand Coat 2-3mm

#### **Description :**

A high build decorative gravity finish based on Acrylic co-polymer and Different sizes of calcium carbonates aggregates, for exterior applications On masonry, concrete panels walls, ceiling and gypsum boards.

#### **Features:**

1. Excellent adhesion strength
2. High film thickness
3. Different patterns by different application
4. No sagging at high film thickness
5. Excellent coverage to minor substrate defects

#### **Physicals Properties:**

Viscosity (Rot thinner at 25 <sup>0</sup> C)	:	above 200 poise
Finish	:	Matt
Flash Point	:	Not applicable
Specific Gravity	:	1.89 kg/L
Solid by Weight	:	80 ± 2
Coverage rate	:	2 – 3kg/m <sup>2</sup> depends on Design Pattern
Dry film thickness	:	Depends on method of application and Required style
Shelf Life (dry and cool store)	:	One year

#### **Surface Preparation and Application Method:**

1. The surface should be dry, free from dirt, oil, grease and powdery material.
2. For old painting, remove the old paint as much as possible.
3. Wash the surface with diluted Ammonia Solution.
4. For new surfaces sand the entire surface and remove the dust.
5. Wash the surface with clean water and allow completing dry.
6. Apply one coat of **EBM EM Exterior Latex Sealer** or **EBM EM Int. & Ext. Primer Sealer**.
7. Fill Holes and Cracks with **EBM EM Wood & Wall Putty**.
8. Apply one coat of **EBM TX Sand Coat 1-2mm** or **Sand Coat 2-3mm**.

**Doha Factory for Paints and Chemicals**

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: [info@dohapaints.com](mailto:info@dohapaints.com). [www.dohapaints.com](http://www.dohapaints.com)

# EBM

Coatings and Chemicals

## Technical Data Sheet

**EBM TX Sand Coat**

**TX4003**  
Sand Coat 1-2mm

**TX4004**  
Sand Coat 2-3mm

### Dilution and Application:

Type of thinner	:	Clean water
Percentage of thinning	:	0 - 5% by volume
Tools	:	Special Trowel

### Drying time (at 25°C):

Touch dry	:	2 – 3 hours
Hard dry	:	10 – 12 hours

### Subsequent Coats:

**EBM EM Top Coat Clear**  
**EBM EM Exterior Acrylic Emulsion**  
**EBM AC Acrylic-Poly Urethane Top Coat 2k**

Colors: EBM Texture Coating Color Cards

Packing: 25 kg/drum

### Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 5°C and relative humidity less than 85%

After Application

- Clean all tools used immediately with water
- Close the cans after used
- Store in dry and cool area

For more information, don't hesitate to contact our Technical Department.

**Doha Factory for Paints and Chemicals**

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: [info@dohapaints.com](mailto:info@dohapaints.com). [www.dohapaints.com](http://www.dohapaints.com)