

EBM

Coatings and Chemicals

Technical Data Sheet

EBM TX Ultra Coat Stone

TX4005

Description : A fine type spray finish based on Veova co-polymer and Special Fillers, For exterior applications on masonry, concrete panels walls, ceiling and Gypsum boards.

Features:

1. Excellent adhesion strength
2. High durability
3. Different patterns by different application
4. No sagging at high film thickness
5. Excellent coverage to minor substrate defects

Physicals Properties:

Viscosity (Rot thinner at 25 ⁰ C)	:	160 - 180 poise
Finish	:	Matt
Flash Point	:	Not applicable
Specific Gravity	:	1.66 kg/L
Solid by Weight	:	78 ± 2
Coverage rate	:	0.5 – 1.0kg/m ² depends on Design Pattern
Dry film thickness	:	Depends on spray and required style
Shelf Life (dry and cool store)	:	One year

Surface Preparation and Application Method:

1. The surface should be dry, free from dirt, oil, grease and powdery material.
2. For old painting, remove the old paint as much as possible.
3. Wash the surface with diluted Ammonia Solution.
4. For new surfaces sand the entire surface and remove the dust.
5. Wash the surface with clean water and allow completing dry.
6. Apply one coat of **EBM EM Exterior Latex Sealer** or **EBM EM Int. & Ext. Primer Sealer**.
7. Fill Holes and Cracks with **EBM EM Wood & Wall Putty**.
8. Apply one coat of **EBM TX Ultra Coat Stone**.

Doha Factory for Paints and Chemicals

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: info@dohapaints.com. www.dohapaints.com

EBM

Coatings and Chemicals

Technical Data Sheet

EBM TX Ultra Coat Stone

TX4005

Dilution and Application:

Type of thinner	:	Clean water
Percentage of thinning	:	0 - 5% by volume
Tools	:	Special Spray Gun

Drying time (at 25°C):

Touch dry	:	2 – 3 hours
Hard dry	:	10 – 12 hours

Subsequent Coats:

EBM EM Top Coat Clear
EBM EM Exterior Acrylic Emulsion
EBM AC Acrylic-Poly Urethane Top Coat 2k

Colors: White and Selected Colors

Packing: 25 kg/drum

Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 5°C and relative humidity less than 85%

After Application

- Clean all tools used immediately with water
- Close the cans after used
- Store in dry and cool area

For more information, don't hesitate to contact our Technical Department.

Doha Factory for Paints and Chemicals

Tel-44504119 - Fax: 44510566 - P.O.Box:35409. New Industrial Area-Doha Qatar

E-mail: info@dohapaints.com. www.dohapaints.com