

Technical Data Sheet

| Description : A superior quality 100% Pure Acrylic based Matt. Emulsion Paint For interior and exterior use, on cement plaster, concrete gypsum plast Gypsum boardetc. | | | |
|---|-------------------------------|------------------------------------|--|
| Features: 1. Excellent resistance to 2. Highly resistant to Ba 3. Durable and highly wa 4. Excellent hiding powe | cterial and Fun ishable | | |
| Physicals Properties: | -+ 2 5 ⁰ C) | 05 110 771 | |
| Viscosity (KREB VISCO. Finish | at 25°C) . | 95 – 110 KU Matt | |
| Flash Point | • | Not applicable | |
| Specific Gravity | | $1.35 \pm 0.02 \text{ kg/L}$ | |
| Solid by Volume | : | 41 ± 2 | |
| Ph value | : | 8.50 - 9.50 | |
| Coverage rate | : | $12 - 14 \text{ m}^2/\text{Liter}$ | |
| Dry film thickness | : | 30 - 40 micron | |
| Shelf Life (dry and cool st | ore) : | One year | |

- 1. The surface should be dry, free from dirt, oil, grease and powdery material.
- 2. For old painting, remove the old paint as much as possible.
- 3. Wash the surface with diluted Ammonia Solution.
- 4. For new surfaces sand the entire surface and remove the dust.
- 5. Wash the surface with clean water and allow to complete dry.
- 6. Apply one coat of **EBM** Acrylic Primer.
- 7. For new surface, apply two coats of **EBM** wood and wall putty, for old painting fill holes and Crack with **EBM** wood and wall putty
- 8. Sand the surface to complete smooth and remove the dust.
- 9. Apply two coats of EBM Pure Acrylic Matt.

Doha Factory For Paints And Chemicals Telephone. +974-44504-119 Fax +974-4460-2832 P.O. Box: 35409, New Industrial Area

1

Email info@dohapaints.com Website www.dohapaints.com



Technical Data Sheet

EBM Pure Acrylic Matt

Dilution and Annlication.

| <u>ilution and Application:</u> | | |
|---------------------------------|--------------|--|
| Type of thinner | : | Clean water |
| Percentage of thinning | : | 15 - 20% by volume |
| Tools | : | Brush or Roller |
| EBM Pure Acrylic Matt can | be also used | l by Air spray gun and Air less spray gun. |

Drying time (at 25°C):

| Touch dry | : | 2-3 hours |
|--------------------------------|---|-----------|
| Hard dry | : | 4-6 hours |
| A second coat can be applied a | S | |

Subsequent Coats:

NONE

Colors: EBM Color Card

Packing: 18 Liter drum, 15 Liter drum, 3.75 Liter Gallon

Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 5^oC and relative humidity less than 85%

After Application

- Clean all tools used immediately with water
- Close the cans after used
- Store in dry and cool area

EM4002