

Coatings and Chemicals

Technical Data Sheet

EBM EM Hi Gloss Emulsion

EM4090

<u>Description</u>: A high-Quality water-based Gloss Emulsion paint for interior and exterior

Applications on cement plaster, concrete, Facade, asbestos and gypsum

board.

Features:

1. Flexible and smooth finish

2. Highly resistant to weathering conditions

3. Excellent scrub resistance and highly washable

4. Good Color retention

Physicals Properties:

Viscosity (KREB VISCO. at 25^oC) : 95 - 110 KU Finish **High Gloss** Flash Point Not applicable Specific Gravity $1.15 \pm 0.02 \text{ kg/L}$ 34.0 ± 1.0 Solid by Volume (%) 8.50 - 9.50Ph value Coverage rate $10 - 12 \text{ m}^2/\text{Liter}$ 30 - 40 micron Dry film thickness Shelf Life (dry and cool store) One year

Surface Preparation and Application Method:

- 1. The surface should be dry, free from dirt, oil, grease and powdery material.
- 2. For old painting, remove the old paint as much as possible.
- 3. Wash the surface with diluted Ammonia Solution.
- 4. For new surfaces sand the entire surface and remove the dust.
- 5. Wash the surface with clean water and allow to completely dry.
- 6. Apply one coat of **EBM** Acrylic Primer.
- 7. For new surface, apply two coats of **EBM** wood and wall putty, for old painting fill holes and Crack with **EBM** wood and wall putty
- 8. Sand the surface to complete smooth and remove the dust.
- 9. Apply two coats of **EBM** Hi Gloss Emulsion.



Coatings and Chemicals

Technical Data Sheet

EBM Hi Gloss Emulsion

EM4090

Dilution and Application:

Type of thinner : Clean water

Percentage of thinning : 5 - 10% by volume Tools : Brush or Roller

EBM Hi Gloss Emulsion can be also used by Air spray gun and Air less spray gun.

Drying time (at 30°C):

Touch dry : 1-2 hours Hard dry : 4-6 hours

A second coat can be applied after six hours

Subsequent Coats:

NONE

Colors: EBM Color Card

Packing: 18 Liter drum, 15 Liter drum, 3.75 Liter Gallon

Remarks:

Before Application

- Stir thoroughly
- Check Temperature above 5°C and relative humidity less than 85%

After Application

- Clean all tools used immediately with water
- Close the cans after used
- Store in dry and cool area

For more information, don't hesitate to contact our Technical Department.